

## NL-R730 - Coating

## **Technical Data Sheet**

Product Description	
Colour Index Name	Pigment Red 104
Colour Index No.	77605
CAS Number	12656-85-8
Chemical Name	Lead (Sulfo) Molybdated Chromate/ Scarlet Chrome



<b>Physical Properties</b>		
Parameter	Values	Method
Specific gravity	6 gm/cm3	IS 33 1992
Oil absorption	24 g/100 g (±5 g)	IS 33 1992
pH of aqueous extract	6 - 8	IS 33 1992
Moisture content	Max. 1.0 %	IS 33 1992
Residue on sieve (45 µm)	Max. 0.5 %	IS 33 1992
Water soluble salts	Max. 1.0 %	IS 33 1992
Conductivity	Max. 500 μS	IS 33 1992
Soluble Pb - content	Max. 1.0 %	IS 3711

Structural Formula
PbCrO4 * PbSO4 * PbMoO4

Fastness Properties		
Parameter	Values	Method
Heat stability ( 5 min )	250°C - 260°C	VX/FP/002
Acid resistance (1-5)	4	IS 2932
Alkali resistance (1-5)	4	IS 2932
Light fastness(1-8)		
Full shade	7 - 8	IS 33 1992
Weather fastness (1-5)		
Full shade	4 - 5	ISO 11341
Resistance to sulphur dioxide (1-5)	4	ISO-3231
Resistance to sulphur dioxide (1 - 5)	4	ISO-3231

Alkyd / Stoving	
Industrial	٠
Coil Coating	٠
Automotive / Refinish / Roaf Marking	٠
Powder Coating	

O - Potential use

NILCHEM is a registered trademark of Nilgoon Pigment Co. The product details and application guidelines provided are based on our extensive research and technological advancements. While these insights reflect our current understanding, they are not legally binding. It is the processing company's responsibility to ensure each product's suitability for their specific applications. As the use of our products is beyond our control, we cannot accept liability for their performance in particular applications.

Company Name: Nilgoon Pigment Co. (NILI CHEM) Address: Sharif University Science & Technology Park, Tehran, Iran





Phone: +98 21-66064604